

Approval body for construction products  
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and  
Länder Governments



## European Technical Assessment

**ETA-18/0383**  
**of 6 September 2018**

English translation prepared by DIBt - Original version in German language

### General Part

Technical Assessment Body issuing the  
European Technical Assessment:

Trade name of the construction product

Product family  
to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment  
contains

This European Technical Assessment is  
issued in accordance with Regulation (EU)  
No 305/2011, on the basis of

Deutsches Institut für Bautechnik

fischer Injection system FIS P Plus

Bonded fastener for use in concrete

fischerwerke GmbH & Co. KG  
Otto-Hahn-Straße 15  
79211 Denzlingen  
DEUTSCHLAND

fischerwerke

18 pages including 3 annexes which form an integral part  
of this assessment

EAD 330499-00-0601

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

## Specific Part

### 1 Technical description of the product

The fischer injection system FIS P Plus is a bonded anchor consisting of a cartridge with injection mortar fischer FIS P Plus and a steel element according to Annex A 3.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

### 2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex C 1 to C 3
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1 and C 2
Displacements (static and quasi-static loading)	See Annex C 3
Characteristic resistance and displacements for seismic performance categories C1 and C2	No performance assessed

#### 3.2 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

### 4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD 330499-00-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1




**5      Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document**

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 6 September 2018 by Deutsches Institut für Bautechnik


BD Dipl.-Ing. Andreas Kummerow  
Head of Department

*beglaubigt:*  
Baderschneider


Installation conditions part 1		
fischer anchor rod		
Pre positioned installation		
		
Push through installation (annular gap filled with mortar)		
		
Pre-positioned or push through installation with subsequently pressed filling disk (annular gap filled with mortar)		
		
Figures not to scale		
<div><div><math>h_0</math> = drill hole depth</div><div><math>t_{fx}</math> = thickness of fixture</div></div> <div><math>h_{ef}</math> = effective embedment depth</div>		
fischer injection system FIS P Plus		Annex A 1
Product description Installation conditions part 1		

## Overview system components part 1


**Injection cartridge (shuttle cartridge) with sealing cap; Size: 345 ml, 360 ml, 390 ml, 550 ml, 950 ml, 1500 ml**



**Injection cartridge (coaxial cartridge) with sealing cap; Size: 100 ml, 150 ml, 300 ml, 380 ml, 400 ml, 410 ml**



**Static mixer FIS MR Plus or UMR**



**Injection adapter and Extension tube for static mixer**



**Cleaning brush BS / BSB**



**Blow-out pump ABG or ABP**



Figures not to scale

fischer injection system FIS P Plus

### System description

Overview system components part 1;  
cartridges / static mixer / accessories

**Annex A 2**

## Overview system components part 2

### fischer anchor rod

Size: M8, M10, M12, M16, M20, M24



### washer / hexagon nut



### fischer filling disk FFD with injection adapter



Figures not to scale

fischer injection system FIS P Plus

### System description

Overview system components part 2;  
steel components




**Annex A 3**



**Table A4.1: Materials**

Part	Designation	Material		
1	Injection cartridge	Mortar, hardener, filler		
	Steel grade	Steel, zinc plated	Stainless steel A4	High corrosion resistant steel C
2	Anchor rod	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$ , EN ISO 4042:1999 A2K or hot-dip galvanized $\geq 40 \mu\text{m}$ EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50 or 80 EN ISO 3506-1:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$ , EN ISO 4042:1999 A2K or hot-dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014
4	Hexagon nut	Property class 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$ , ISO 4042:1999 A2K or hot-dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
5	fischer filling disk FFD similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$ , EN ISO 4042:1999 A2K or hot-dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014



Specifications of intended use (part 1)				
Table B1.1: Overview use and performance categories				
Anchorages subject to		FIS P Plus with ...		
		Anchor rod 		
Hammer drilling with standard drill bit 		all sizes		
Hammer drilling with hollow drill bit (Heller "Duster Expert"; Bosch "Speed Clean"; Hilti "TE-CD, TE-YD") 		Nominal drill bit diameter (d <sub>0</sub> ) 12 mm to 28 mm		
Static and quasi static load, in uncracked concrete		all sizes	Tables: C1.1 C2.1 C3.1 C3.2	
Use category	I1	dry or wet concrete	all sizes	
	I2	Flooded hole	M12 to M24	
Installation direction		D3 (downward and horizontal and upwards (e.g. overhead) installation)		
Installation temperature		T <sub>i,min</sub> = 0 °C to T <sub>i,max</sub> = +40 °C		
In-service temperature	Temperature range I	-40 °C to +40 °C	(max. short term temperature +40 °C ; max. long term temperature +24 °C)	
	Temperature range II	-40 °C to +80 °C	(max. short term temperature +80 °C ; max. long term temperature +50 °C)	
fischer injection system FIS P Plus			Annex B 1	
Intended use Specifications (part 1)				

## Specifications of intended use (part 2)

### Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres of strength classes C20/25 to C50/60 according to EN 206:2013

### Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure, to permanently damp internal conditions or in other particular aggressive conditions (high corrosion resistant steel)

Note: Particular aggressive conditions are e. g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e. g. in desulphurization plants or road tunnels where de-icing materials are used)

### Design:

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages are designed in accordance with FprEN 1992-4:2017 and EOTA Technical Report TR 055

### Installation:

- Anchor installation is to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- In case of aborted hole: The hole shall be filled with mortar
- Anchorage depth should be marked and adhered to on installation
- Overhead installation is allowed

fischer injection system FIS P Plus

**Intended use**  
Specifications (part 2)

**Annex B 2**

**Table B3.1:** Installation parameters plus minimum spacing and minimum edge distance for anchor rods

Anchor rods		Thread	M8	M10	M12	M16	M20	M24
Width across flats	SW	[mm]	13	17	19	24	30	36
Nominal drill hole diameter	$d_0$		10	12	14	18	24	28
Drill hole depth	$h_0$		$h_0 = h_{ef}$					
Effective embedment depth	$h_{ef, min}$		60	60	70	80	90	96
	$h_{ef, max}$		160	200	240	320	400	480
Minimum spacing and minimum edge distance	$s_{min} = c_{min}$		40	45	55	65	85	105
Diameter of the clearance hole of the fixture	pre positioned installation $d_f$		9	12	14	18	22	26
	push through installation $d_f$		11	14	16	20	26	30
Minimum thickness of concrete member	$h_{min}$		$h_{ef} + 30 (\geq 100)$			$h_{ef} + 2d_0$		
Maximum torque moment for attachment of the fixture	$\max T_{fx}$	[Nm]	10	20	40	60	120	150


**fischer anchor rod**



**Marking (on random place) fischer anchor rod:**

Property class 8.8, stainless steel, property class 80 and high corrosion resistant steel, property class 80: •  
Stainless steel A4, property class 50 and high corrosion resistant steel, property class 50: ••  
Alternatively: Colour coding according to DIN 976-1

**Installation conditions:**



**Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled**

- Materials, dimensions and mechanical properties according to Annex A 4, Table A4.1
- Inspection certificate 3.1 according to EN 10204:2004, the documents have to be stored
- Setting depth is marked

Figures not to scale

fischer injection system FIS P Plus

**Intended use**  
Installation parameters anchor rods

**Annex B 3**

**Table B4.1:** Parameters of the cleaning brush BS (steel brush)

The size of the cleaning brush refers to the drill hole diameter

Nominal drill hole diameter	$d_0$	[mm]	10	12	14	18	24	28
Steel brush diameter	$d_b$		11	14	16	20	26	30



**Table B4.2** Maximum processing time of the mortar and minimum curing time  
(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature)

Temperature at anchoring base [°C]	Maximum processing time $t_{work}$	Minimum curing time $t_{cure}$
>±0 to +5	13 min	3 h
>+5 to +10	9 min	90 min
>+10 to +20	5 min	60 min
>+20 to +30	4 min	45 min
>+30 to +40	2 min	35 min

<sup>1)</sup> In wet concrete or water filled holes the curing times must be doubled

fischer injection system FIS P Plus

**Intended use**







Cleaning brush (steel brush)  
Processing time and curing time

**Annex B 4**





## Installation instructions part 1

### Drilling and cleaning the hole (hammer drilling with standard drill bit)

1		Drill the hole. Nominal drill hole diameter $d_0$ and drill hole depth $h_0$ see <b>tables B3.1</b>
2		Clean the drill hole: For $h_{eff} \leq 12d$ and $d_0 < 18$ mm blow out the hole four times by hand
		For $h_{eff} > 12d$ and / or $d_0 \geq 18$ mm blow out the hole four times with oil-free compressed air ( $p \geq 6$ bar)
3		Brush the drill hole four times. For deep holes use an extension. Corresponding brushes see <b>table B4.1</b>
4		Clean the drill hole: For $h_{eff} \leq 12d$ and $d_0 < 18$ mm blow out the hole four times by hand
		For $h_{eff} > 12d$ and / or $d_0 \geq 18$ mm blow out the hole four times with oil-free compressed air ( $p \geq 6$ bar)

Go to step 5

### Drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		Check a suitable hollow drill (see <b>table B1.1</b> ) for correct operation of the dust extraction
2		Use a suitable dust extraction system, e. g. Bosch GAS 35 M AFC or a comparable dust extraction system with equivalent performance data  Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Nominal drill hole diameter $d_0$ and drill hole depth $h_0$ see <b>tables B3.1</b>

Go to step 5






fischer injection system FIS P Plus

**Intended use**  
Installation instructions part 1




**Annex B 5**

## Installation instructions part 2

### Preparing the cartridge

5		Remove the sealing cap Screw on the static mixer (the spiral in the static mixer must be clearly visible)	
6			Place the cartridge into the dispenser
7			Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey

### Injection of the mortar

8			
	Fill approximately 2/3 of the drill hole with mortar. Always begin from the bottom of the hole and avoid bubbles	For drill hole depth $\geq 150$ mm use an extension tube	For overhead installation, deep holes ( $h_0 > 250$ mm) use an injection-adaptor








fischer injection system FIS P Plus

**Intended use**  
Installation instructions part 2

**Annex B 6**

### Installation instructions part 3

#### Installation of anchor rods

9		<p>Only use clean and oil-free anchor elements. Mark the setting depth of the anchor. Push the anchor rod down to the bottom of the hole, turning it slightly while doing so. After inserting the anchor element, excess mortar must be emerged around the anchor element.</p>			
	 <p>For overhead installations support the anchor rod with wedges. (e. g. fischer centering wedges)</p>	 <p>For push through installation fill the annular gap with mortar</p>			
10	 <p>Wait for the specified curing time <math>t_{\text{cure}}</math> see <b>table B4.2</b></p>	<td data-bbox="890 824 983 1010">11</td> <td data-bbox="983 824 1302 1010">  </td> <td data-bbox="1302 824 1522 1010"> <p>Mounting the fixture max <math>T_{\text{fix}}</math> see <b>tables B3.1</b></p> </td>	11		<p>Mounting the fixture max <math>T_{\text{fix}}</math> see <b>tables B3.1</b></p>
Option		<p>After the minimum curing time is reached, the gap between anchor and fixture (annular clearance) may be filled with mortar via the fischer filling disc FFD. Compressive strength <math>\geq 50 \text{ N/mm}^2</math> (e.g. fischer injection mortars FIS HB, FIS SB, FIS V, FIS EM Plus, FIS P Plus) <b>ATTENTION:</b> Using fischer filling disc FFD reduces <math>t_{\text{fix}}</math> (usable length of the anchor)</p>			

fischer injection system FIS P Plus

**Intended use**  
Installation instructions part 3

**Annex B 7**



Table C1.1: Essential characteristic for the <b>steel bearing capacity</b> under tensile / shear load of <b>fischer anchor rods</b> and <b>standard threaded rods</b>										
Anchor rod / standard threaded rod			M8	M10	M12	M16	M20	M24		
Bearing capacity under tensile load, steel failure <sup>3)</sup>										
Characteristic resistance $N_{Rk,s}$	Steel zinc plated	Property class	5.8	[kN]	19 (17)	29 (27)	43	79	123	177
			8.8		29 (27)	47 (43)	68	126	196	282
	Stainless steel A4 and high corrosion resistant steel C		50		19	29	43	79	123	177
			70		26	41	59	110	172	247
			80		30	47	68	126	196	282
Partial factors <sup>1)</sup>										
Partial factor $\gamma_{M2,t}$	Steel zinc plated	Property class	5.8	[-]	1,50					
			8.8		1,50					
	Stainless steel A4 and high corrosion resistant steel C		50		2,86					
			70		1,50 <sup>2)</sup> / 1,87					
			80		1,60					
Bearing capacity under shear load, steel failure										
without lever arm <sup>3)</sup>										
Characteristic resistance $V_{Rk,s}$	Steel zinc plated	Property class	5.8	[kN]	9 (8)	15 (13)	21	39	61	89
			8.8		15 (13)	23 (21)	34	63	98	141
	Stainless steel A4 and high corrosion resistant steel C		50		9	15	21	39	61	89
			70		13	20	30	55	86	124
			80		15	23	34	63	98	141
Ductility factor			$k_7$	[-]	1,0					
with lever arm <sup>3)</sup>										
Charact. resistance $M_{Rk,s}^0$	Steel zinc plated	Property class	5.8	[Nm]	19 (16)	37 (33)	65	166	324	560
			8.8		30 (26)	60 (53)	105	266	519	896
	Stainless steel A4 and high corrosion resistant steel C		50		19	37	65	166	324	560
			70		26	52	92	232	454	784
			80		30	60	105	266	519	896
Partial factors <sup>1)</sup>										
Partial factor $\gamma_{M2,v}$	Steel zinc plated	Property class	5.8	[-]	1,25					
			8.8		1,25					
	Stainless steel A4 and high corrosion resistant steel C		50		2,38					
			70		1,25 <sup>2)</sup> / 1,56					
			80		1,33					
<sup>1)</sup> In absence of other national regulations <sup>2)</sup> Only admissible for steel C, with $f_{yk} / f_{uk} \geq 0,8$ and $A_5 > 12 \%$ (e.g. fischer anchor rods) <sup>3)</sup> Values in brackets are valid for undersized threaded rods with smaller stress area $A_s$ for hotdip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009.										
fischer injection system FIS P Plus								Annex C 1		
<b>Performances</b> Essential characteristics for the steel bearing capacity of fischer anchor rods and standard threaded rods										

Table C2.1: Essential characteristics under tensile / shear load									
Size			All sizes						
Tensile load									
Uncracked concrete		$k_{ucr,N}$	[-]	11,0					
Factors for the compressive strength of concrete > C20/25									
Increasing factor for $\tau_{pk}$	C25/30	$\Psi_c$	[-]	1,05					
	C30/37			1,10					
	C35/45			1,15					
	C40/50			1,19					
	C45/55			1,22					
	C50/60			1,26					
Splitting failure									
Edge distance	$h / h_{ef} \geq 2,0$	$c_{cr,sp}$	[mm]	$1,0 h_{ef}$					
	$2,0 > h / h_{ef} > 1,3$			$4,6 h_{ef} - 1,8 h$					
	$h / h_{ef} \leq 1,3$			$2,26 h_{ef}$					
Spacing		$s_{cr,sp}$		$2 c_{cr,sp}$					
Concrete cone failure									
Edge distance		$c_{cr,N}$	[mm]	$1,5 h_{ef}$					
Spacing		$s_{cr,N}$		$2 c_{cr,N}$					
Installation factor tensile load		$\gamma_{inst}$	[-]	1,2					
Shear load									
Installation factor shear load		$\gamma_{inst}$	[-]	1,0					
Concrete pry-out failure									
Factor for pry-out failure		$k_B$	[-]	2,0					
Calculation diameters									
Size				M8	M10	M12	M16	M20	M24
fischer anchor rods and standard threaded rods		$d_{nom}$	[mm]	8	10	12	16	20	24
fischer injection system FIS P Plus								Annex C 2	
Performances Essential characteristics under tensile / shear load									

Table C3.1: Essential characteristics of tensile resistance for fischer anchor rods and standard threaded rods in hammer drilled holes; uncracked concrete									
Anchor rod / standard threaded rod			M8	M10	M12	M16	M20	M24	
Combined pullout and concrete cone failure									
Calculation diameter		d	[mm]	8	10	12	16	20	24
Uncracked concrete									
Characteristic bond resistance in uncracked concrete C20/25									
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)									
Temperature range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	7,5	7,5	7,5	7,5	7	7
	II: 50 °C / 80 °C			6,5	6,5	6,5	6,5	6	6
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole)									
Temperature range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	---	---	7,5	7,5	7	7
	II: 50 °C / 80 °C			---	---	6,5	6,5	6	6
Installation factors									
Dry or wet concrete		$\gamma_{inst}$	[-]	1,0					
Flooded hole				1,2 <sup>1)</sup>					
<sup>1)</sup> Only with coaxial cartridges: 380ml, 400 ml, 410 ml									

Table C3.2: Displacements for anchor rods							
Anchor rod		M8	M10	M12	M16	M20	M24
Displacement-Factors for tensile load <sup>1)</sup>							
Uncracked concrete; Temperature range I, II							
$\delta_{ND}$ -Factor	[mm/(N/mm <sup>2</sup> )]	0,09	0,09	0,10	0,10	0,10	0,10
$\delta_{Ncr}$ -Factor		0,10	0,10	0,12	0,12	0,12	0,13
Displacement-Factors for shear load <sup>2)</sup>							
Uncracked concrete; Temperature range I, II							
$\delta_{VD}$ -Factor	[mm/kN]	0,11	0,11	0,10	0,10	0,09	0,09
$\delta_{Vcr}$ -Factor		0,12	0,12	0,11	0,11	0,10	0,10
<sup>1)</sup> Calculation of effective displacement: $\delta_{ND} = \delta_{ND-Factor} \cdot \tau_{Ed}$ $\delta_{Ncr} = \delta_{Ncr-Factor} \cdot \tau_{Ed}$ ( $\tau_{Ed}$ : Design value of the applied tensile stress)				<sup>2)</sup> Calculation of effective displacement: $\delta_{VD} = \delta_{VD-Factor} \cdot V_{Ed}$ $\delta_{Vcr} = \delta_{Vcr-Factor} \cdot V_{Ed}$ ( $V_{Ed}$ : Design value of the applied shear force)			

fischer injection system FIS P Plus		Annex C 3
Performances Essential characteristics of tensile resistance for fischer anchor rod, standard threaded rods (uncracked concrete), Displacement for anchor rods		